

The physical property values of Polycon[®] 06A

Properties	ASTM	Unit	Value
Tensile Strength	D4894	PSI [MPa]	2,800 [19.3]
Tensile Modulus	D4894	PSI [MPa]	-
Elongation	D4894	%	200
Compressive Strength ¹	D695	PSI [MPa]	3,000 [20.7]
Compressive Modulus	D695	PSI [MPa]	-
Deformation Under Load ²	D621	%	5
Hardness	D2240	Shore D	64
Specific Gravity	D792	-	2.26
Coefficient of Friction	-	-	0.1

1. Compressive Strength was tested at 10% strain.
2. Deformation Under Load was tested at 2,000 psi for 24 hours.
3. All testing is performed at room temperature unless otherwise specified.

NOTE: The information contained herein are typical values which falls within the normal range of properties. All information are intended for reference and comparison purposes only as general guideline for use at user discretion. They should not be used as a basis for design specifications or quality control. Polymer Concepts do not guarantee any specific result and assume no obligation or liability for any advice furnished by it or for results obtained with respect to the products.

Material

- Lubricated Glass-Filled Modified PTFE

Features/Benefits

- Excellent heat and wear resistance
- Can be abrasive running against soft metals at high surface speed
- Recommended for high pressure hydraulic service

Working Temperature Range

- -450°F to +600°F
[-268°C to +316°C]

Color

- Dark Gray

Polymer Concepts Technologies, Inc.
13522 Manhasset Road
Apple Valley, CA 92308
Phone: (760) 240-4999
Fax: (760) 240-4399

Email: pcti@polymerconcepts.com
Website: www.polymerconcepts.com
Inquiries: (844) 300-7900
©2023 Polymer Concepts Technologies, Inc.

AS 9100D & ISO 9001 Certified